Designation: A 167 - 99 (Reapproved 2004)

Standard Specification for Stainless and Heat-Resisting Chromium-Nickel Steel Plate, Sheet, and Strip¹

This standard is issued under the fixed designation A 167; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

- 1.1 This specification covers stainless and heat-resisting chromium-nickel steel plate, sheet, and strip.
- 1.2 The values stated in inch-pound units are to be regarded as the standard.

Note 1—Grades that were previously covered in both Specifications A 167 and A 240/A 240M have been removed from this specification and may now be supplied and purchased in compliance with Specification A 240/A 240M. The chemical and mechanical property requirements of these grades were identical in Specifications A 167 and A 240/A 240M at the time of removal from Specification A 167.

2. Referenced Documents

- 2.1 ASTM Standards: ²
- A 240/A 240M Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications
- A 370 Test Methods and Definitions for Mechanical Testing of Steel Products
- A 480/A 480M Specification for General Requirements for Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip
- E 527 Practice for Numbering Metals and Alloys (UNS) 2.2 SAE Standard:³

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.17 on Flat-Rolled and Wrought Stainless Steel.

J 1086 Numbering Metals and Alloys (UNS)

3. Chemical Composition

3.1 The steel shall conform to the requirements as to chemical composition specified in Table 1, and shall conform to applicable requirements specified in Specification A 480/A 480M.

4. Mechanical Properties

4.1 The material shall conform to the mechanical properties specified in Table 2.

5. General Requirements

- 5.1 The following requirements for orders for material furnished under this specification shall conform to the applicable requirements of the current edition of Specification A 480/A 480M.
 - 5.1.1 Definitions,
 - 5.1.2 General requirements for delivery,
 - 5.1.3 Ordering information,
 - 5.1.4 Process,
 - 5.1.5 Heat treatment,
 - 5.1.6 Special tests,
 - 5.1.7 Dimensions and permissible variations,
 - 5.1.8 Workmanship, finish, and appearance,
 - 5.1.9 Number of tests,
 - 5.1.10 Specimen preparation,
 - 5.1.11 Retreatment,
 - 5.1.12 Inspection,
 - 5.1.13 Rejection and rehearing,
 - 5.1.14 Material test report,
 - 5.1.15 Certification, and
 - 5.1.16 Packaging, marking, and loading.

Current edition approved Sept. 1, 2004. Published September 2004. Originally approved in 1935. Last previous edition approved in 1999 as A 167 – 99.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001.

TABLE 1 Chemical Requirements^A

	Composition, %											
UNS Desig- nation ^B	Туре	Car- bon	Man- ganese	Phos- pho- rus	Sulfur	Silicon	Chromium	Nickel	Molyb- denum	Other Elements		
S30215	302B	0.15	2.00	0.045	0.030	2.00-3.00	17.0–19.0	8.00-10.0		N 0.10		
S30800	308	0.08	2.00	0.045	0.030	0.75	19.0-21.0	10.0-12.0				
S30900	309	0.20	2.00	0.045	0.030	0.75	22.0-24.0	12.0-15.0				
S31000	310	0.25	2.00	0.045	0.030	1.50	24.0-26.0	19.0-22.0				

A Maximum unless range or minimum is indicated.

TABLE 2 Mechanical Property Requirements

UNS Designation ^A	_	Tensile St	rength, min	Yield Stre	ngth, min ^B	Elongation in 2 in. or 50 mm, min, %	Hardness, \max^{C}	
Ü	Type -	ksi	MPa	ksi	MPa		Brinell	Rockwell B
S30215	302B	75	515	30	205	40.0	217	95
S30800	308	75	515	30	205	40.0	183	88
S30900	309	75	515	30	205	40.0	217	95
S31000	310	75	515	30	205	40.0	217	95

^A New designation established in accordance with Practice E 527 and SAE J 1086.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).

^B New designation established in accordance with Practice E 527 and SAE J 1086.

^B Yield strength shall be determined by the offset method at 0.2 % in accordance with Test Methods and Definitions A 370. Unless otherwise specified, an alternative method of determining yield strength may be based on a total extension under load of 0.5 %.

^C Either Brinell or Rockwell B hardness is permissible.